

# EUROPEAN PATENT OFFICE

## Patent Abstracts of Japan

PUBLICATION NUMBER : 58126679  
PUBLICATION DATE : 28-07-83


APPLICATION DATE : 22-01-82  
APPLICATION NUMBER : 57007595

APPLICANT : HITACHI LTD;

INVENTOR : KUDO TETSUICHI; ✓

INT.CL. : H01M 10/40

TITLE : FORMATION OF ELECTRODE FOR  
THIN-FILM LITHIUM BATTERY



ABSTRACT : PURPOSE: To obtain an electrode, which has an excellent electric contact and a high mechanical adhesion, by interposing beforehand a film made of the original metal of a positive electrode material between the positive electrode material and a positive current-collecting body of a thin-film lithium battery, the positive electrode of which is prepared from a metal chalcogenide or a metal oxide.

CONSTITUTION: After a titanium film 2 with about  $0.1\mu\text{m}$  thickness is formed on an iron plate 1 with  $0.4\text{mm}$  thickness,  $\text{TiS}_2$  is formed on the film 2 into a film 3 of around  $3\mu\text{m}$  thickness by the CVD method. Next, a solid electrolyte material represented by the formula,  $(1-X)\text{Li}_4\text{SiO}_4 \times \text{Li}_3\text{PO}_4$  ( $0 < X < 1$ ), is formed over the film 3 into a film 4 with around  $2\mu\text{m}$  thickness by sputtering. After that, lithium is formed on the film 4 into a film 5 with around  $1\mu\text{m}$  thickness by a vapor-deposition method, thereby obtaining a basic structure for a thin-film lithium battery. As a result of measurement carried out in a dry atmosphere on the basic characteristics of the battery such as open-circuit voltage and short-circuit current, at room temperature, an open-circuit voltage of  $2.4\text{V}$  and a short-circuit current of  $3\text{mA}/\text{cm}^2$  were obtained.

COPYRIGHT: (C)1983,JPO&Japio